Searching by Document Number

שמווושאו וושוווסס האווונייושביי

```
modified, fluoro-fatty acid modified, fatty acid modified, alkyl aralkyl
                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                              PURPOSE: To obtain a thermal transfer sheet capable of forming an image
                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                            of high density at a high speed by incorporating a releasable silicone
                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                  1-20 pts.wt. per 100 pts.wt. of a dye forming resin. When the addition
                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                    silicone resins is desirable and the addition amount thereof is pref.
                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                              of the discoloration or preservability of a dye is generated. At the
                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                        layer is formed to the surface of a base film and an image receiving
                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                    CONSTITUTION: As the silicone resin used in a dye layer, for example,
                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                     polyether modified, epoxy/polyether modified and polyether modified
                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                     dye transfer properties and film strength are lowered or a problem
                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                             time of thermal transfer, a thermal transfer sheet wherein the dye
                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                               a modified silicone resin selected from epoxy modified, long chain
                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                        amount is too little, release effect is insufficient and, when the
                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                      F-term: 2H111AA01,AA05,AA15,AA27,AA33,AA47,BA03,BA39,BA53,BA55,BA63,BB04,
                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                    sheet wherein a dye receiving layer is provided to the surface of
                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                             because
                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                              alkyl modified, alkyl modified, carboxyl modified, higher alcohol
                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                          addition amount is too much, no pref. result is obtained,
                                                                                                                                                                              1990-196692[1990/08/03]
                                                                                          1989- 15074[1989/01/26]
                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                      Inventor: AKATA MASANORI, EGASHIRA NORITAKA, NAKAMURA YOSHINORI
                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                         Title of invention: THERMAL TRANSFER SHEET AND METHOD
     1/
** Result [Patent] ** Format(P805) 22.Aug.2003
                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                       BB05, BB06, CA03, CA23, CA25, CA30, CA33, CA41
                                                                                                                                                                                                                                                                                                                       Examined publication date (present law):
                                                                                                                                                                                                                          Examined publication no/date (old law):
                                                                                                                                                                                                                                                                                                                                                                                                                                                          Applicant: DAINIPPON PRINTING CO LTD
                                                                                                                                   Date of request for examination:
                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                        resin in a dye layer.
                                                                                                                                                                                    Public disclosure no/date:
                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                          ,1017
                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                  Fixed keyword: R124,R125
                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                      Expanded classification:
                                                                                                                                                                                                                                                                                                                                                                                                                 PCT publication no/date
                                                                                                                                                                                                                                                                                 Registration no/date:
                                                                                             Application no/date:
                                                                                                                                                                                                                                                                                                                                                                      PCT application no
                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                5/26
                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                    B41M 5/38
                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                B41M
                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                   Citation:
                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                           Abstract:
                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                          IPC:
```

a base film are superposed so that the dye layer of the thermal transfer sheet is opposed to the receiving layer of the image receiving sheet and heated imagewise from the rear of the thermal transfer sheet. COPYRIGHT: (C)1990,JPO&Japio